



EPO DYNWEIGHT BAL-XV-FS

BALANCING COMPOUND

MIXING INSTRUCTIONS AND PRODUCT DESCRIPTION

EPO Dynaweight BAL-XV-FS is a two-part epoxy putty. Thoroughly mix equal parts (**by volume or weight**) of Red Part "A" and Yellow Part "B" until the mass is an even uniform orange color.

EPO Dynaweight BAL-XV-FS is a fast-curing compound that has a **working pot life of approximately 15 to 20 minutes and will set hard in 25 to 30 minutes at room temperature.**

No change occurs during cure, except hardening.

Shelf life of separate components is one year from date of shipment in unopened containers at temperatures between 70° and 90° F.

EPO Dynaweight BAL-XV-FS should be mixed and applied using latex or similar gloves. Direct skin contact should be avoided.

EPO Dynaweight BAL-XV-FS will withstand temperatures ranging from -80° F to 311° F.

Area where **EPO Dynaweight BAL-XV-FS** is to be applied must be free of grease, oil or other contaminates.

Store above 70° F